



Product Sheet

ABS Plain Colour Edgings - UNI

ABS plain colour edgings are extruded, thermoplastic edges of high quality made from a thermal, mechanically stable thermoplastic - ABS (Acrylonitrile-Butadiene-Styrene). It has a protective and decorative function for the edges of furniture boards.

ABS plain colour edgings exhibit good interior colour stability, withstand high mechanical forces, fulfil the most stringent qualitative and ecological standards, are harmless for the human health and do not contain heavy metals and phthalates.

Adhesion Properties:

ABS plain colour edgings are coated with a layer of primer on the reverse that, in connection with suitable glue (based on EVA, PUR, PO or APAO), ensures adhesion to the boards.

Protective Top Coating:

ABS plain colour edgings can be coated with protective layer with different gloss levels to improve scratch resistance to the surface.

ABS Plain Colour Edgings - Parameters:

Thickness Tolerances

Thickness in mm	Tolerance	
0,45 - 0,6 mm	- 0,05 mm	+ 0,05 mm
0,7 - 1 mm	- 0,10 mm	+ 0,10 mm
1,1 - 1,6 mm	- 0,20 mm	+ 0,10 mm
1,7 - 2 mm	- 0,25 mm	+ 0,15 mm
2,1 - 5 mm	- 0,30 mm	+ 0,15 mm

Width Tolerances

Width in mm	Tolerance	
11 - 31 mm	- 0,3 mm	+ 0,5 mm
above 32 mm	- 0,5 mm	+ 0,5 mm

Edging Profile Tolerance*

Profile Tolerance	Internal Test Method
Bottom Side of Edgings	$\leq 0,2$ mm

* slight bent in cross cut profile of the edgings ensures optimal connection to the board due to absorption of the glue in the central part of the edgings and minimizing of the joint between edgings and the board.

Roll Length Tolerance*

	Tolerance
Nominal Length of the Roll	$\pm 1,5$ %

* there can be max. one joint within the roll length. Rolls with joint are marked with green rectangular sticker with wording "joint in the roll" directly on the roll or on the palette.

Plain Linearity

Longitudinal Deformation	Internal Test Method
All Widths	< 3 mm/1 m



Qualitative Characteristics

Properties	Values	Standard
Light Fastness	≥ 6	ČSN EN ISO 4892-2
Softening Point (Vicat B 50)	~ 95 °C	ČSN EN ISO 306
Shrinkage	< 1 % at 85 °C during 1 hour	Internal Test Method
Hardness (Shore type D)	~ 73	ČSN EN ISO 868
Chemical Resistance*	1 B	DIN 68861-1

* exception of acetone and etyl-butyacetate.

Surface Finish - Top Coat

Structure	Surface Pattern	Tolerance
Coated Surface: 6° - 60° of Gloss (max 30° for surfaces wooden pore and pearl)	smooth, wooden pore, pearl	± 5°
Coated Surface: 90° of Gloss	smooth	± 10°

Colour Tolerances*

Colour Shade	L Value	Internal Test Method
White Shades	L ≥ 90	Δ E ≤ 0,8
Light Colours	70 ≤ L < 90	Δ E ≤ 1,0
Dark Colours	L < 70	Δ E ≤ 1,5

* measured with spectrophotometer with D8* geometry and D65 light exposure.

Application of Functional Layer Based on EVA

	Quantity	Tolerance
Colour Shade*	160 g/m ²	± 10%

* please follow information specified in Product Sheet for Functional Layer (PS FL ENG – valid version) – to select right colour and application.
 Width of applied functional layer can be max 1mm narrower (from each side of the edgings) then the width of the edgings.
 Minimum recommended thickness of edgings for transparent functional layer is 0,8 mm (please see PS FL ENG – valid version)
 Minimum recommended thickness of edgings for transparent functional layer is 1 mm.

Application of Hot Melt Based on EVA

	Quantity	Tolerance
Colour Shade*	160 g/m ²	± 10%

* contact your sales representative for available colours of hot melt layer.



Processing

Technology	Comments
Sawing	yes
Cross Cutting	yes
Top Coating	yes
Radius Milling	yes
Buffing	yes
Pre-Milling	yes
Machine Gluing	yes
Milling Direction	machine direction, opposite direction
Bending 0,45 - 0,9 mm Edging	yes, radius min. 30 mm (min. 50 mm for coated edgings)
Bending 1 mm - 1,5 mm Edging	yes, radius min. 40 mm (min. 60 mm for coated edgings)
Bending 1,6 mm - 2 mm Edging	yes, radius min. 50 mm (min. 60 mm for coated edgings)
Bending 2,1 mm - 3 mm Edging	yes, radius min. 60 mm (min. 60 mm for coated edgings)

Application:

ABS plain colour edgings are suitable for all types of furniture, mainly for areas with high potential of wear. ABS plain colour edgings are specified for interior application.

Gluing Techniques:

- Machine bonded with use of suitable glues - EVA, PO, PUR and APAO.
- Machine bonded with use of laser, hot air or infra-red heating – ABS edgings with applied functional layer, based on EVA or PO that ensures required adhesion to the boards.
- Manual bonding machine with hot air nozzle - ABS edgings with applied functional layer.
- Manually, with use of contact adhesives.

Gluing Conditions:

Moisture level of the edgings and boards should be between 8 – 15%.
Temperature of the boards, edgings and environment during gluing: min. 15°C.

Stress Whitening:

Some colours of ABS plain colour edgings can exhibit stress whitening on the worked surfaces (radius milling mainly). Correct settings of gluing machine and additional buffing can minimize this effect. Contact your local sales representative for more information.



Surface Defects:

Potential surface defects of ABS plain colour edgings are evaluated from the distance of 70cm (potential defects should not affect visual appearance of the surface from this distance). Surface defects can be classified like: black specs, dots, lumps, dents, cracks, waves, colour changes, gloss level changes, etc.

Cleaning:

For cleaning of ABS plain colour edgings from the glue residues we recommend special cleaning agents based on hydrocarbons and alcohol (free of aromatic substances and solvents). We recommend cleaning agents Hraniclean 01 and RI408 for manual cleaning and RI006 LP 163/93 for machine application.

For cleaning of surfaces of ABS plain colour edgings, we recommend standard household cleaners or alcohol (do not use cleaners containing acetone or etyl-butylacetate).

Fine surface structures of ABS plain colour edgings (e.g. pearl) are sensitive to mechanical damage during cleaning process with cleaners and cloths. It can result in white maps on the surface after cleaner evaporation. This effect is standard behaviour of ABS materials and shall not be a reason for quality claim of the product. It is recommended, for return of the surface into original visual appearance, to expose the surface to the heated air flow for the short time period (hair dryer, hot air blower,...).

Storage Conditions:

Store under appropriate conditions – temperature between 15 - 25°C, relative humidity 55 - 60%, in closed packaging to protect against direct sunlight. We strongly recommend making an application trial for the ABS plain colour edgings older than 12 months after delivery date.

Disposal:

ABS plain colour edgings and boards covered with ABS edgings plain colours can be disposed according to the regulation of each country – e.g. incinerated or landfilled.

Information given in this Product sheet are to the best of our knowledge, however are not binding, especially in view of possible property rights of third parties. Company Hranipex will neither directly nor indirectly participate in any compensation of the customer or third party.

Company Hranipex strongly recommends to every customer to execute its own testing of ABS plain colour edgings for the planned methods and application. Indicated data serves for orientation only and do not represent any specification, nor give warranty to the edge banding characteristics.

We keep the right to change or update information in this Product sheet at any time.

HRANIPEX will not directly or indirectly contribute to any indemnification to a buyer or a third party, or in case of third party claims regarding any infringement of intellectual property rights.

In case of multiple language versions, in case of unclear interpretation of information in any part of a language version of this document, the English wording in the original document created by Hranipex CZ shall prevail. Such original translated documents must have the abbreviation HRX HQ in the header and be stored in the Hranipex controlled document database.



Hranipex Czech Republic k.s.
J. Rýznerové 97, Komorovice
396 01 Humpolec
Czech Republic

T +420 565 501 211
F +420 565 501 241-2
M +420 606 789 742, +420 602 167 944
E cz-hranipex@hranipex.com
www.hranipex.cz

Citibank Europe plc
Praha 5, Stodůlky
CZK: 2530240107/2600
EUR: CZ92 2600 0000 0025 3024 0318
Swift: CITICZPX

IČ: 26112361
DIČ: CZ26112361
Registrováno Krajským soudem
v Českých Budějovicích
oddíl A, vložka 8463